

TECHNICAL DATA SHEET*Revision date: 30.10.2024***BASIC AEROSOLS: SPRAY PAINT**

Article number:	26204 (black matt), 26205 (black semi matt), 26206 (white matt), 26214 (black glossy), 26414 (white glossy)						
Colour:	black, white						
Intended use:	Car refinishing product/ Paint						
General characteristics:	<p>1K fast-drying acrylic paint offering excellent coverage and adhesion for different treated and untreated surfaces. The paint has lasting colour and good surface hardness.</p> <ul style="list-style-type: none">▪ non-fading and UV resistant• resistant to petrol, chemicals and de-icing salt▪ wear and scratch resistant <p>Fields of application:</p> <table><tr><td>▪ metal</td><td>▪ aluminium</td><td>▪ wood</td></tr><tr><td>▪ various types of plastic</td><td>▪ glass</td><td>▪ stone</td></tr></table>	▪ metal	▪ aluminium	▪ wood	▪ various types of plastic	▪ glass	▪ stone
▪ metal	▪ aluminium	▪ wood					
▪ various types of plastic	▪ glass	▪ stone					

TECHNICAL CHARACTERISTICS**Base:** acrylic resin**Smell:** characteristic**Gloss:** high glossy/matt/semi matt**Degree of gloss:** glossy >75 GU; matt 10 ±2 GU; semi matt 45 ±5 GU**Consumption:** 1.5 - 2 m²**Temperature resistant:** up to 110°C**APPLICATION PROCESS**

Before use, carefully read and observe the warning texts on the label!

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be from +10 °C to +25 °C and max. air humidity should not exceed 80%.

Processing tips:

- The substrate must be clean, dry, free from rust and grease. Remove old loose coatings or primers
- Beforehand, mask the parts that shouldn't be painted
- Wear a respirator (type A2/P3 is recommended)
- Apply a Chamäleon primer suitable for the surface
- After drying, sand the base layer with P400-P800
- Degrease the surface again
- The aerosol should have room temperature
- Before use, shake the aerosol for 2 min and spray a sample
- Apply the Spray paint in several thin layers
- Distance to the surface should be 25 - 30 cm
- Keep a flash off time 3 - 5 min between each spray pass (depending on the layer thickness)
- Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

Drying	Dust free	Set to touch	Overcoatable
Object temperature 20 °C	5 - 10 min	10 - 20 min	2 h

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

VOC regulation:

EU limit value: Category B/e 840 g/l

This product contains max. 645.3 g/l g/l VOC

Shelf life:

120 months in tightly closed original container at temperatures between +10°C and +25°C

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.