

**TECHNICAL DATA SHEET***Revision date: 06.02.2025***SPRAY PUTTY**

Article number:	26701
Colour:	beige
Intended use:	Car refinishing product/ Priming
General characteristics:	<p>High quality, fast drying filler for filling small imperfections in treated and untreated surfaces. It is ideal for levelling large uneven areas on sanded undercoats. Suitable as a pre-treatment for all paint systems (alkyd, nitrocellulose, 1K acrylic and 2K acrylic).</p> <ul style="list-style-type: none"><li>▪ high filling power and durability</li><li>▪ good flow</li><li>▪ easy to sand</li></ul> <p><b>Substrates:</b></p> <ul style="list-style-type: none"><li>▪ plastics</li><li>▪ metal</li><li>▪ old paint coating</li><li>▪ polyester putties</li></ul>

**TECHNICAL CHARACTERISTICS****Base:** acrylic resin**Smell:** solvent**Consumption:** 1.25 - 1.75 m<sup>2</sup> (400 ml)**DFT:** 70 - 80 µm (3 layers)**Temperature resistant:** up to 110°C**APPLICATION PROCESS**

Before use, carefully read and observe the warning texts on the label!

**Processing conditions:**

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be from +12 °C to +25 °C and max. air humidity should not exceed 80%.

## Processing tips:

- The substrate must be clean, dry, free from dust and grease. Remove old loose coatings and primers
- Beforehand, mask the parts that shouldn't be painted
- Degrease the surface
- Wear a respirator (type A2/P3 is recommended)
- The aerosol should have room temperature
- Before use, shake the aerosol for 2 min and spray a sample
- Distance to the surface should be approximately 15 - 20 cm
- Apply Spray putty in 3 layers
- Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

### ATTENTION:

- After sanding thoroughly clean surface with water-based cleaner
- Don't use solvent-based cleaner
- Not recoatable with PVB/Acid based primers

Drying	Dust free	Set to touch	Re-coatable
Object temperature 20 °C	5 min	15 - 20 min	60 min
Object temperature 60 °C			20 min
IR-Drying mediumwave*			20 min

\*The temperature of the object should not be more than 60 - 70 °C

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

## Sanding:

Dry sandind with P 600-800

## VOC regulation:

EU limit value: Category B/e 840 g/l

This product contains max 675.5 g/l VOC

## Shelf life:

120 months, if stored in tightly closed original container

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.